# **TP CAULKING GUNS**

# Product Description

**TP Caulking Guns** Cartridge, Foil, and Bulk Loading

Features:

Industrial grade

| Item Number | Description                  |
|-------------|------------------------------|
| TP 1525     | TP Caulking Gun 10.3oz.      |
| TP 1526     | TP Caulking Gun 30oz.        |
| TP 1527     | TP Caulking Foil Gun 20.2oz. |
| TP 1528     | TP Caulking Foil Gun tips    |
| TP 1529     | TP Bulk Loading Gun 24oz.    |

# TP FS MORTAR



TP Firestop Mortar is a specially formulated rapid hardening gypsum/cement compound. The product provides the optimum combination of workability, strength and fire resistance. When mixed with clean water to a suitable consistency, TP Firestop Mortar sets without shrinking and can form a rigid, gas tight, fire resistant seal. It can easily be drilled and resealed if future penetrants are needed. No special tools are required to mix or install the product. TP Firestop Mortar systems are rated for up to 4 hours and has been tested in accordance with ASTM E814 (UL 1479) test standard.

TP Firestop Mortar is protected in a wet stage as well as in a dry stage against mold growth with a combination of biocides.

### Use TP Firestop Mortar for various applications:

- Wall or floor applications
- Around metallic pipes (steel, copper, iron, etc.)
- Around electrical power cables
- Around communication cables (telephone, fiber optic, etc.)
- Blank openings
- Concrete or concrete block (CMU) walls
- Concrete floors
- Cable Trays (aluminum or steel)

| Item Number | Description  | Size       |
|-------------|--------------|------------|
| TP 1520     | TP FS Mortar | 45 lbs.bag |

# <section-header><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text><text>

### **TP Firestop Mortar Features:**

- Non-sag Adjustable consistency (pourable or trowelable)
- High yield
- Non-shrinking
- Safe and simple to use
- Workable approximately 45 minutes

# Material Properties

| Color                            | Light Red                                      |
|----------------------------------|--|
| Approximate expansion on setting | 0.1%   |
| Density loose bulk               | 40.6 pcf (650 kg/m³)                           |
| Density wet cast                 | 84.3 pcf (1350 kg/m <sup>3</sup> )             |
| Density oven dried               | 54.6 pcf (875 kg/m³)                           |
| Crushing strength, wet           | 700 psi (5 N/mm²)                              |
| Asbestos fillers                 | None   |
| PH Values                        | 6.5  |
| Adhesion to concrete             | Excellent                                      |
| Adhesion to Steel/Copper         | Good   |
| Adhesion to Cables               | Good   |
| Freeze-Thaw Resistance           | Excellent                                      |
| Workable Pot Life                | Approximately 45 minutes                       |
| Sets hard                        | 3 - 4 hours                                    |
| Fully Cured                      | 28 days  |
| Yield                            | 2:1 mix ratio, 1500 cubic inches per 45 lb bag |
|                                  | 3:1 mix ratio, 1350 cubic inches per 45 lb bag |

# Applications

A fire rated load bearing mortar to economically firestop large openings for through-penetrations in fire rated walls and floors. Can be used with power cables, fiber optic telephone cables. Recommended for use with aluminum or steel cable trays, as well as EMT, copper, steel, or black iron pipe.

# Installation Data

Mixing Procedure: Mix with clean water in a suitable container. Slowly add the dry mortar mix to water while stirring by hand, or by power mixer, to ensure a smooth lump free mix.

Recommended Mixing Ratios: Mortar Mix: Water (by volume) Consistency

- Pourable For Floor Openings 2 1/2: 1
- Stiff for Wall Openings 3: 1

### DO NOT USE A MIX RATIO OF LESS THAN 2:1

**Note:** The wet mix will remain usable for approximately 45-60 minutes depending on batch size, water content and temperature. Once material has been mixed to the desired consistency, DO NOT attempt to alter by adding additional water or mortar THIS WILL CAUSE THE MATERIAL TO HARDEN VERY QUICKLY. Any spillage should be wiped up with a damp cloth before setting occurs.

### **Thickness/Fire Rating**

Refer to tested designs or manufacturer's recommendations.

### Health and Safety

Non-toxic and asbestos free. Take normal precautions to avoid inhalation, or ingestion, and to ensure adequate ventilation when mixing. In the event of eye or mouth contact, wash immediately with plenty of clean water. Refer to Safety Data Sheet for additional information.

### Contains: Gypsum Plaster and Perlite aggregate.

INSTALLATION INSTRUCTIONS WALL OPENINGS For small holes and gaps, trowel a stiff mix into the opening to the desired depth. For larger holes, use an appropriate damming material to support the mix until it sets.

### **Floor Openings**

When sealing holes in floor slabs, an appropriate damming material must be installed prior to pouring in the mortar mix. Panels of damming materials should be cut to fit tightly around penetration within the opening so as to avoid leakage of the mortar mix during pouring.

**Note:** Damming materials can be made from various materials, e.g. insulation, hard foam, wood, backer rod, etc. These damming materials can be either combustible or noncombustible. Combustible damming material is usually removed after the mortar mix has set. Non-combustible damming materials can be left in place. However, the specifier or the local authority having jurisdiction may require a specific type of or the removal of a particular damming material. If damming material is to be removed, a suitable bond breaker (e.g. plastic sheeting) should be used between the mortar mix and the damming material.

# Testing Data

TP Firestop Mortar has been classified and listed by Underwriters Laboratories and tested at a positive pressure with a minimum .01 inches of water and in accordance with ASTM E814 (UL 1470).

# Storage & Handling

Must be stored in dry conditions under protective cover in its original container. Two year shelf life when stored inside, in a conditioned area and in the original unopened containers.

# Limitations

TP Firestop Mortar is not designed to be used in areas under continuous immersion or in areas which would be continuously wet. The mortar should not be used in areas which would experience high or severe vibration or movement.

# Cautions

For chemical emergency, spill, leak, fire, exposure or accident, get immediate medical attention.

Precautions: Do not take internally. May cause eye, skin, and respiratory tract irritation. Wear gloves and safety glasses. Wash after handling. FIRST AID: For any over exposure or if skin irritation develops get immediate medical attention after first aid is given.
EYES: Flush for 15 minutes with clean water. Seek immediate medical attention. SKIN: Wash with soap and water. Do not use solvents to remove from skin. INHALATION: Remove to fresh air. INGESTION: DO NOT INDUCE VOMITING. SPILLS: Clean up immediately with scrapers and water. STORAGE AND HANDLING Keep container upright and tightly closed. Do not reuse container.
KEEP OUT OF REACH OF CHILDREN.

For additional information, refer to Safety Data Sheet. For additional technical service: www.team-pro.com or info@team-pro.com

# Limited Warranty

TEAM PRO makes the Limited Express Warranty that when the instructions for storage and handling of our products are followed we warrant our products to be free from defects. THIS LIMITED EXPRESS WARRANTY IS EXPRESSLY IN LIEU OF ANY OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND OF ANY OTHER OBLIGATION ON THE PART OF TEAM PRO. The sole remedy for breach of the Limited Express Warranty shall be the refund of the purchase price. All other liability is negated and disclaimed, and TEAM PRO shall not be liable for incidental or consequential damages.

Suggestions and recommendations covering the use of our products are based on our laboratory findings. However, as we have no control as to the methods and conditions of application, we only assume responsibility for the uniformity of our products within manufacturing tolerances.